

Technical Data Sheet

LubX[®] CV - ASTM

Typical characteristics

- Excellent dry-running properties
- Good machinability
- Excellent sliding properties even at higher load
-
- Good wear resistance

Typical industries

- Mechanical Engineering Industry
- Paper Industry
- Conveyor Technology & Automation
- Food Industry
- Bakery and Confectionery
- Beverage Industry

	Test method	Unit	Guideline value
General properties			
Water Absorption	ASTM D570	%	<0.01
Mechanical properties			
Hardness	ASTM D2240	Shore D	60
Tensile Strength at yield 73°F	ASTM D638	psi	2700
Elongation at Break	ASTM D638	%	>250
Thermal properties			
CTE, linear	ASTM D696	1/K	1.0x10 ⁻⁴
Melting Point		°F	275
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	108
Flammability, UL94		1/8 inch	HB
Electrical properties			
Volume Resistivity	ASTM D257	Ωcm	>10 ¹⁴
Surface resistivity	ASTM D257	Ohm/cm	≥10 ¹²
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
rep@roechling-plastics.us • www.roechling.com/industrial/rep-us

Print: 31/07/2023 • Draft: 15/02/2023

PIM-Version: 24 • PIM-ID: 717942 • PIM-Code: 24-10-11.68.9.8.141-3.3.8.3.3-2

Page 2 / 2 (Dates in DD/MM/YYYY)

