

Technical Data Sheet

Polystone® ABS - ASTM

Typical characteristics

- High rigidity
- Good impact strength
- Chemical resistance

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	1.03
Water Absorption	ASTM D570	%	0.3
Mechanical properties			
Tensile Strength at yield 73°F	ASTM D638	psi	5600
Tensile Modulus	ASTM D638	psi	301000
Flexural Modulus	ASTM D790	psi	313000
Rockwell Hardness	ASTM D785	R	102
Izod Impact, Notched	ASTM D256	ft-lb/in	8.0
Coefficient of Friction, Dynamic			0.35
Thermal properties			
CTE, linear	ASTM D696	in/in/°F	4.89x10 ⁻⁴
Maximum Service Temperature, Air permanent		°F	222
Heat Deflection Temperature 264psi	ASTM D648	°F	168
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM DI50	1MHz	3.2
Dielectric strength	ASTM DI49		450
Surface resistivity	ASTM D257	Ohm/cm	10 ¹⁴
Compliance properties			
FDA			Yes
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
rep@roechling-plastics.us • www.roechling.com/industrial/rep-us

Print: 31/07/2023 • Draft: 17/02/2023

PIM-Version: 29 • PIM-ID: 717954 • PIM-Code: 29-22-9.160.26-2

Page 2 / 2 (Dates in DD/MM/YYYY)

