



PIEDMONT MARINE GRADE

AQUAPLAS®

FOAMED AQUA-PLAS® II

PMG Foamed Aqua-Plas II HDPE is created through an extrusion process using heat and pressure, which transforms co-polymer high density polyethylene pellets into sheets of various thicknesses.

MATERIAL INFORMATION

Current Thickness Production Capability:

- .200" to 1.5"

Current Sheet Size Production Capability:

- max. 75" wide x 216" long - min. 36" x 36"
(max./min. varies with thickness)

Tolerance Information:

- Gauges: +/- 5%
- Length: +.25"/-0" (at room temperature)
- Width: +.25"/-0" (at room temperature)



PROPERTIES	UNITS	NATIONAL VALUES	ASTM
Density	g/cc	0.955	D1505
Tensile Strength @ Yield	psi	>4,100	D638
Tensile Modulus	psi	250,000	D638
Elongation @ Break	%	>600	D638
Elongation @ Yield	%	9.8	D638
Flexural Modulus	psi	185,000	D790
Flexural Stress @ 5% Strain	psi	3,810	D790
Compressive Properties @ 10% Strain	psi	4,950	D695
Durometer	Shore D	68	D2240
Tensile Impact	ft.lbs/in ²	115	D1822
Izod Impact Resistance	ft.lbs/in ²	1.1	D256
Brittleness Temp.	°C/°F	<-76°C (<-105°F)	D746
Vicat Softening	°C/°F	123°C(253°F)	D1525
Heat Deflection Temp. 66 psi	°C/°F	75°C (167°F)	D648
Coefficient of Linear Thermal Expansion	10 ⁻⁶ in/in C deg	155	D696
Anti-Skid Wet Coefficient of Friction	%	.60	D2047

CONTACT US

800.277.7898 Toll Free | 704.597.8200
5010 W. W.T. Harris Blvd | Charlotte, NC 28269
www.piedmontplastics.com