

HYDEX® 202 natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PU (Polyurethane)

Colour

beige

Density

1.2 g/cm³

Main features

- high dimensional stability
- broad chemical compatibility
- good impact strength
- good mechanical properties
- easy to machine

Target Industries

- medical technology
- chemical technology
- fixture construction
- pharmaceutical industry
- oil and gas industry
- process engineering

Mechanical properties

condition

value

test method

comment

Modulus of elasticity (tensile test)	@ 73 °F	240,000	psi	ASTM D 638
Tensile strength at yield	@ 73 °F	9000	psi	ASTM D 638
Tensile strength at break	@ 73 °F	8000	psi	ASTM D 638
Elongation at break (tensile test)	@ 73 °F	80	%	ASTM D 638
Flexural strength	@ 73 °F	12,000	psi	ASTM D 790
Modulus of elasticity (flexural test)	@ 73 °F	260,000	psi	ASTM D 790
Compression strength	@ 73 °F, 1% strain	1,200	psi	ASTM D 695
Compression strength	@ 73 °F, 10% strain	12,000	psi	ASTM D 695
Compression modulus	@ 73 °F	180,000	psi	ASTM D 695
Impact strength (Izod)	@ 73 °F	10	ft-lbs/in	ASTM D 256
Rockwell hardness	M Scale	88		ASTM D 785
Coefficient of friction	Static (vs. steel)	0.26		ASTM D 3702
Coefficient of friction	Dynamic (vs. steel)	0.22		ASTM D 3702
Thermal properties	condition	value	test method	comment
Vicat softening point		292	°F	ASTM D 1525
Deflection temperature	@ 66 psi	290	°F	ASTM D 648
Deflection temperature	@ 264 psi	280	°F	ASTM D 648
Service temperature		280	°F	-
Thermal expansion (CLTE)		3.7*10 ⁻⁵	in/in/°F	ASTM D 696
Other properties	condition	value	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.12	%	ASTM D 570

→ Resin specification:

Ensinger Internal Specification

Shapes specification:

NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2016/10/24

Version: A0