

NP310E

TECHNICAL DATA BULLETIN

GRADE: NP310E

NEMA LI 1-1998 Grade: CE

U.L. LISTED: N

DESCRIPTION: Manufactured with a cotton fabric and phenolic resin, NP310E is easy to machine and possesses lower moisture absorption and enhanced electrical properties. NP310E is certifiable to ANSI/NEMA IM 60000-2021 Grade CE, MIL-I-24768/14, and ASTM D709 Type II Grade CE.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.37
Rockwell Hardness (ASTM D785)0.250" Build-up		M Scale	100		
Moisture Absorption (ASTM D570)Condition D ₁ -24/23		%	2.00		
Flexural Strength (ASTM D790)Condition A LW / CW		psi (MPa)	17,500 / 15,000 (120.7) / (103.4)		
Flexural Modulus (ASTM D790)Condition A LW / CW		kpsi (GPa)	1,600 / 1,500 (11.0) / (10.3)		
Tensile Strength (ASTM D638)Condition A LW / CW		psi (MPa)		11,000 / 9,000 (75.8) / (62.1)	
Izod Impact Strength (ASTM D256)Condition A LW / CW Condition E-48/50 LW / CW		ft-lb/in (J/cm)			
		ft-lb/in (J/cm)			1.70 / 1.50 (0.91) / (0.80)
Compressive Strength (ASTM D695)Condition A Flatwise		psi (MPa)			34,000 (234.4)
Bonding Strength (ASTM D229)Condition A Condition D-48/50		lb (kg)			2,500 (1,134.0)
		lb (kg)			2,100 (952.5)
Shear Strength (ASTM D732)Condition A Perpendicular		psi (MPa)	14,000 (96.5)		

TECHNICAL DATA BULLETIN

GRADE: NP310E

NEMA LI 1-1998 Grade: CE

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
THERMAL PROPERTIES					
Temperature Index ¹ (UL Bulletin 746b)	Electrical / Mechanical	°C	115 / 125		
Coefficient of Thermal Expansion (IPC-TM 650-2.4.24)	X-axis / Y-axis	" / °C x10 ⁻⁶		20.0 / 22.0	
Flammability Rating (UL Bulletin 94)	Condition A	Class	HB		
ELECTRICAL PROPERTIES					
Breakdown Voltage (ASTM D149)	Condition A	kVolts	40		
	Condition D-48/50	kVolts	3		
Electric Strength (ASTM D149)	Condition A	Volts/mil (kV/cm)	550 (216.5)		
	Condition D-48/50	Volts/mil (kV/cm)	300 (118.1)		
Arc Resistance (ASTM D495)	Condition A	sec		15	

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.