

## TECATRON® PVX - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PPS (Polyphenylsulfide)

### Colour

black opaque

### Density

1.5 g/cm<sup>3</sup>

### Fillers

carbon fibres, PTFE, graphite

### Main features

- very good bearing and wear properties
- very good chemical resistance
- good heat deflection temperature
- inherent flame resistance
- high dimensional stability
- high stiffness
- high creep resistance

### Target Industries

- mechanical engineering
- aircraft and aerospace technology
- automotive industry
- conveyor technology
- precision engineering
- textile industry

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	1 mm/min	667,000 psi	DIN EN ISO 527-2	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	7,700 psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	50 mm/min	7700 psi	DIN EN ISO 527-2	(3) Data obtained from public source
Elongation at break (tensile test)	50 mm/min	1.5 %	DIN EN ISO 527-2	
Flexural strength	2 mm/min	13,200 psi	DIN EN ISO 178	
Modulus of elasticity (flexural test)	2 mm/min	696,000 psi	DIN EN ISO 178	
Compression strength	2% strain 5 mm/min	5220 psi	EN ISO 604	
Compression strength	1% strain 5 mm/min	2760 psi	EN ISO 604	
Compression modulus	@ 73 °F	479,000 psi	ASTM D 695	2)
Impact strength (Izod)	@ 73 °F	6.7 ft-lbs/in	-	3)
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Melting temperature		538 °F	DIN 53765	
Service temperature	Intermittent	500 °F	-	
Service temperature	Long Term	446 °F	-	
Thermal expansion (CLTE)	72 - 140 F extrusion direction	2.8*10 <sup>-5</sup> in/in/°F	DIN EN ISO 11359-1;2	
Specific heat		0.215 BTU/lb-F°	ISO 22007-4:2008	
Thermal conductivity		4.03 %	ISO 22007-4:2008	
<i>Electrical properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
surface resistivity		10 <sup>4</sup> -10 <sup>10</sup> Ω	DIN EN 61340-2-3	
volume resistivity		10 <sup>7</sup> -10 <sup>12</sup> Ω*cm	DIN EN 61340-2-3	
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.02 %	ASTM D 570	(1) estimated
Flammability (UL94)		V0	-	1)

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).