



PLEXIGLAS®
BY ARKEMA

Plexiglas® P55

CELL CAST ACRYLIC SHEET

PLEXIGLAS® P55 CELL CAST ACRYLIC SHEET (COLORLESS)

Thickness	Sheet Size
0.125"	Made to Order
0.250"	Made to Order
0.500"	Made to Order
0.750"	Made to Order
1.000"	Made to Order
1.250"	Made to Order
1.500"	Made to Order
1.750"	Made to Order
2.000"	Made to Order

Plexiglas® P55 cell cast acrylic sheet is a made to order item. Please check with your local sales person for sheet size options, availability and production schedules.

Additional thicknesses can be quoted upon request.

Plexiglas® P55 cell cast acrylic sheet is produced by Altuglas International. It is manufactured to meet the requirements of MIL-PRF-8184F, Type I and II, Class 1. Typical markets include general aviation and military aircraft. Applications include aircraft canopies, instrument panels, and lens covers. It is available in thicknesses ranging from 0.125" to 2.000".

- **A Premium grade, cross-linked cell-cast acrylic sheet suitable for stretching for Mil-Spec applications**
- **Can be used alone or as a laminate**
- **Lightweight – Half the weight of glass**
- **Weather resistant**
- **Excellent light transmission and optical clarity**
- **Easily fabricated and thermoformed**

Distributed by:

 **Piedmont Plastics®**
where solutions take shape

Toll Free: 1.800.277.7898
www.piedmontplastics.com

ALTUGLAS
INTERNATIONAL
ARKEMA GROUP

Plexiglas® P55

CELL CAST ACRYLIC SHEET



Typical Standard Properties

PROPERTIES	TEST METHOD	UNITS	VALUE
Physical			
Nominal Thickness for data unless otherwise noted	N/A	in	0.500"
Specific Gravity	ASTM D-792	N/A	1.19
Water Absorption (24 hours) ²	ASTM D-570	%	< 0.20
Optical			
Refractive index @ 72°F	ASTM D-542	N/A	1.49
Luminous Transmittance ¹	ASTM D-1003	%	92.5
Luminous Transmittance – After 1000 hrs accelerated weathering ¹	ASTM D-1003	%	92.5
Haze – Initial ¹	ASTM D-1003	%	< 2.0
Haze – After 1000 hrs accelerated weathering ¹	ASTM D-1003	%	< 3.0
UV Transmission (290-330 nm) ¹	MIL-PRF-8184F	%	< 0.5
Angular Deviation (Primary)	ASTM F-733	Minutes	3
Effect of Accelerated Weathering on Appearance (crazing, discoloration, warping)	ASTM D-1449	Visual	None
Mechanical			
Tensile Strength, yield	ASTM D-638	psi	11,600
Tensile Elongation, break	ASTM D-638	%	3.5
Residual Shrinkage (Internal Strain)	ASTM D-4802	%	< 1.0
Thermal			
Deflection Temperature Under Flexural Load @ 264 psi	ASTM D-638	°F	229
Coefficient of Linear Thermal Expansion	ASTM E-831	in / in °C	0.00006
Maximum Recommended Continuous Service Temperature	N/A	°F	180
Recommended Thermoforming Temperature	N/A	°F	290-360
Craze Resistance			
Dry Substrate: Isopropyl Alcohol	MIL-PRF-8184F	psi	2800
Dry Substrate: Toluene : Isobutyl Acetate (1:2)	MIL-PRF-8184F	psi	2800
Wet Substrate: Isopropyl Alcohol	MIL-PRF-8184F	psi	1800
Wet Substrate: Toluene : Isobutyl Acetate (1:2)	MIL-PRF-8184F	psi	1800
Flammability³ & Specification Compliance			
Horizontal Burn Rate	ASTM D-635	in / min	0.50
Military Performance Specification	MIL-PRF-8184F	---	PASS

- Data given are typical average values and should not be used for specification purposes
- All samples conditioned for at least 40 hours at 23°C +/- 2°C and 50% RH +/- 10%

1. This property will change with thickness. The value given is for the thickness indicated in the column heading unless otherwise noted.
2. Water absorption samples conditioned for 1 hour at 110°C.
3. Flammability tests are small scale tests and may not be indicative of how materials will perform in an actual situation.

Plexiglas® acrylic plastic is a combustible thermoplastic. Observe fire precautions appropriate for comparable forms of wood and paper. For building uses, check code approvals. Impact resistance is a factor of thickness. Avoid exposure to heat or aromatic solvents. Clean with soap and water. Avoid abrasives.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations.
Altuglas® and Plexiglas® are registered trademarks of Arkema.
©2013 Arkema Inc. All rights reserved.