

# Technical data sheet



## Polystone® M (UHMW-PE) Reprocessed

### Product characteristics

- High abrasion and wear resistance
- Low coefficient of friction
- Economical grade

### Typical field of application

- Wear strips
- Chute and hopper liners
- Chain guides

	ASTM Test method	Unit	Value
<b>Physical Properties</b>			
Specific Gravity	D792	g/cm <sup>3</sup>	0.94
Water Absorption	D570	%	≤0.01
<b>Mechanical Properties</b>			
Hardness	D785	Shore D	65
Tensile Strength at yield 73 °F	D638	psi	3000
Tensile Modulus	D638	psi	100,000
Elongation at Break	D638	%	≥ 290
Flexural Strength	D790	psi	80,000
Compressive Strength	D695	psi	2800
Izod Impact, Notched	D256	ft-lb/in	No Break
Coefficient of Friction, Dynamic	-	-	0.15 - 0.20
Coefficient of Friction, Static	-	-	0.20 - 0.25
Wear Resistance	Sand Slurry	-	130
<b>Thermal properties</b>			
CTE, linear	D696	in/in°F	1.1 x 10 <sup>-4</sup>
Melting Point	D3418	°F	275°
Maximum Service Temperature, Air	-	°F	180°
Deflection Temperature at 1.8Mpa (264psi)	D648	°F	116
Flammability, UL94	-	1/8 inch	HB
<b>Electrical properties</b>			
Dielectric constant	D150	-	2.3
Surface resistivity	D257	Ohm/cm	>10 <sup>15</sup>
Dielectric strength	D149	V/mil	45
<b>Compliance Properties</b>			
FDA	-	-	No
NSF	-	-	No
USDA	-	-	No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Distributed by:



Toll Free: 1.800.277.7898  
[www.piedmontplastics.com](http://www.piedmontplastics.com)

