



SH82

Product Information

● *Product Description*

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives.

SH82 film is available in a range of thickness from 200ga to 700ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● *Typical Properties*

Property	Unit	Value							Test Method
General									
Nominal Thickness	Gauge (μm)	200 (50)	265 (67)	300 (75)	380 (96.5)	400 (100)	460 (116.8)		SKC Method
Mechanical									
Tensile Strength	Kpsi	MD	28.5	27.0	26.5	25.5	25.5	25.0	ASTM D882
		TD	33.0	33.0	32.0	30.0	30.0	29.0	
Elongation At Break	%	MD	165	180	180	185	185	190	ASTM D882
		TD	125	130	130	140	140	140	
Surface									
Coefficient of Friction	μk (Kinetic) μs (Static)		0.38	0.38	0.39	0.39	0.39	0.39	ASTM D1894
Surface Tension	Dyne	Chemical	36	36	36	36	36	36	ASTM D 2578
Optical									
Haze	%		0.90	1.00	1.10	1.30	1.40	1.50	ASTM D1003
Light Transmission	%		90.3	90.2	90.2	90.1	90.1	90.0	ASTM D1003
Gloss	%		190	190	190	190	190	187	ASTM D523 ASTM D 1003
Thermal									
Heat Shrinkage	%	MD	1.0	1.0	1.0	1.0	1.0	1.0	SKC Method (150°Cx30 min)
		TD	0.6	0.6	0.6	0.6	0.6	0.6	

* Unit Correlation : $\text{N/mm}^2 = \text{Kg/mm}^2 \times 9.8$

$\text{Kg/mm}^2 = \text{Kpi} / 1.4223$

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee.

Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.

Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82

Product Information

● *Product Description*

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives.

SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● *Typical Properties*

Property	Unit	Value						Test Method
General								
Nominal Thickness	Gauge (μm)	500 (125)	600 (150)	650 (165)	700 (175)	750 (188)		SKC Method
Mechanical								
Tensile Strength	Kpsi	MD TD	25.0 29.0	24.0 28.0	23.0 27.0	22.0 26.0	21.0 25.5	ASTM D882
Elongation At Break	%	MD TD	195 140	215 145	235 150	250 150	255 150	ASTM D882
Surface								
Coefficient of Friction	μk (Kinetic) μs (Static)		0.39 0.43	0.39 0.43	0.39 0.43	0.39 0.43		ASTM D1894
Surface Tension	Dyne	Chemical	36	36	36	36		ASTM D 2578
Optical								
Haze	%		1.60	1.70	1.80	2.10	2.70	ASTM D1003
Light Transmission	%		90.0	89.9	89.5	89.5	88.9	ASTM D1003
Gloss	%		185	180	180	180	175	ASTM D523 ASTM D 1003
Thermal								
Heat Shrinkage	%	MD TD	1.0 0.6	0.9 0.5	0.9 0.5	0.9 0.5		SKC Method (150°C x 30 min)

* Unit Correlation : $\text{N/mm}^2 = \text{Kg/mm}^2 \times 9.8$

$\text{Kg/mm}^2 = \text{Kpi} / 1.4223$

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee.

Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.

Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (200ga)

Product Information

● **Product Description**

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications. **SH82** film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value		Test Method
General				
Nominal Thickness	(Gauge) μm	200 (50)		SKC Method
Mechanical				
Tensile Strength	psi (Kg/mm ²)	MD TD	28,500 (20) 33,000 (23)	ASTM D 882
Elongation At Break	%	MD TD	165 125	ASTM D 882
Surface				
Coefficient of Friction	μk (Kinetic) μs (Static)			ASTM D1894
Surface Tension	Dyne Chemical			ASTM D 2578
Optical				
Haze	%			ASTM D 1003
Light Transmission	%			ASTM D 1003
Gloss	%			ASTM D 523
Thermal				
Heat Shrinkage	%	MD TD	1.0 0.6	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8
Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (265ga)

Product Information

● **Product Description**

Skyrol® **SH82** is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value		Test Method
General				
Nominal Thickness	(Gauge) μm	265 (67)		SKC Method
Mechanical				
Tensile Strength	psi (Kg/mm ²)	MD TD	27,000 (19) 33,000 (23)	ASTM D 882
Elongation At Break	%	MD TD	180 130	ASTM D 882
Surface				
Coefficient of Friction	μk (Kinetic) μs (Static)			ASTM D1894
Surface Tension	Dyne Chemical			ASTM D 2578
Optical				
Haze	%			ASTM D 1003
Light Transmission	%			ASTM D 1003
Gloss	%			ASTM D 523
Thermal				
Heat Shrinkage	%	MD TD	1.0 0.6	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8
Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com

SH82 (300ga)

Product Information

● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. SH82 film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications. SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● Typical Properties

Property	Unit	Value		Test Method
General				
Nominal Thickness	(Gauge) μm	300 (75)		SKC Method
Mechanical		MD	TD	
Tensile Strength	psi (Kg/mm ²)	26,500 (19)	32,000 (22)	ASTM D 882
Elongation At Break	%	MD	180	ASTM D 882
		TD	130	
Surface				
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43		ASTM D1894
Surface Tension	Dyne	Chemical	36	ASTM D 2578
Optical				
Haze	%	1.10		ASTM D 1003
Light Transmission	%	90.2		ASTM D 1003
Gloss	%	190		ASTM D 523
Thermal				
Heat Shrinkage	%	MD	1.0	SKC Method
		TD	0.6	(150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (380ga)

Product Information

● **Product Description**

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value		Test Method
General				
Nominal Thickness	(Gauge) μm	380 (96.5)		SKC Method
Mechanical		MD	TD	
Tensile Strength	psi (Kg/mm ²)	25,500 (18)	30,000 (21)	ASTM D 882
Elongation At Break	%	MD	TD	ASTM D 882
Surface				
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43		ASTM D1894
Surface Tension	Dyne	Chemical	36	ASTM D 2578
Optical				
Haze	%	1.30		ASTM D 1003
Light Transmission	%	90.1		ASTM D 1003
Gloss	%	190		ASTM D 523
Thermal		MD	TD	
Heat Shrinkage	%	1.0 0.6		SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (400ga)

Product Information

● **Product Description**

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value		Test Method
General				
Nominal Thickness	(Gauge) μm	400 (100)		SKC Method
Mechanical				
Tensile Strength	psi (Kg/mm ²)	MD TD	25,500 (18) 30,000 (21)	ASTM D 882
Elongation At Break	%	MD TD	185 140	ASTM D 882
Surface				
Coefficient of Friction	μk (Kinetic) μs (Static)		0.39 0.43	ASTM D1894
Surface Tension	Dyne	Chemical	36	ASTM D 2578
Optical				
Haze	%		1.40	ASTM D 1003
Light Transmission	%		90.1	ASTM D 1003
Gloss	%		190	ASTM D 523
Thermal				
Heat Shrinkage	%	MD TD	1.0 0.6	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (460ga)

Product Information

● **Product Description**

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value	Test Method
General			
Nominal Thickness	(Gauge) μm	460 (116.8)	SKC Method
Mechanical			
Tensile Strength	psi (Kg/mm ²)	MD TD 25,000 (18) 29,000 (20)	ASTM D 882
Elongation At Break	%	MD TD 190 140	ASTM D 882
Surface			
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne	Chemical 36	ASTM D 2578
Optical			
Haze	%	1.50	ASTM D 1003
Light Transmission	%	90.0	ASTM D 1003
Gloss	%	187	ASTM D 523
Thermal			
Heat Shrinkage	%	MD TD 1.0 0.6	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (500ga)

Product Information

● **Product Description**

Skyrol® **SH82** is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value	Test Method
General			
Nominal Thickness	(Gauge) μm	500 (125)	SKC Method
Mechanical			
Tensile Strength	psi (Kg/mm ²)	MD TD 25,000 (18) 29,000 (20)	ASTM D 882
Elongation At Break	%	MD TD 195 140	ASTM D 882
Surface			
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne	Chemical 36	ASTM D 2578
Optical			
Haze	%	1.60	ASTM D 1003
Light Transmission	%	90.0	ASTM D 1003
Gloss	%	185	ASTM D 523
Thermal			
Heat Shrinkage	%	MD TD 1.0 0.6	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (600ga)

Product Information

● Product Description

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● Typical Properties

Property	Unit	Value	Test Method
General			
Nominal Thickness	(Gauge) μm	600 (150)	SKC Method
Mechanical			
Tensile Strength	psi (Kg/mm ²)	MD TD 24,000 (17) 28,000 (20)	ASTM D 882
Elongation At Break	%	MD TD 215 145	ASTM D 882
Surface			
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
Optical			
Haze	%	1.70	ASTM D 1003
Light Transmission	%	89.9	ASTM D 1003
Gloss	%	180	ASTM D 523
Thermal			
Heat Shrinkage	%	MD TD 0.9 0.5	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet (MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (650ga)

Product Information

● **Product Description**

Skyrol® **SH82** is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications. **SH82** film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value	Test Method
General			
Nominal Thickness	(Gauge) μm	650 (165)	SKC Method
Mechanical			
Tensile Strength	psi (Kg/mm ²)	MD TD 23,000 (16) 27,000 (19)	ASTM D 882
Elongation At Break	%	MD TD 235 150	ASTM D 882
Surface			
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne Chemical	36	ASTM D 2578
Optical			
Haze	%	1.80	ASTM D 1003
Light Transmission	%	89.5	ASTM D 1003
Gloss	%	180	ASTM D 523
Thermal			
Heat Shrinkage	%	MD TD 0.9 0.5	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8
Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (700ga)

Product Information

● **Product Description**

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value	Test Method
General			
Nominal Thickness	(Gauge) μm	700 (175)	SKC Method
Mechanical			
Tensile Strength	psi (Kg/mm ²)	MD TD 22,000 (15) 26,000 (18)	ASTM D 882
Elongation At Break	%	MD TD 250 150	ASTM D 882
Surface			
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne	Chemical 36	ASTM D 2578
Optical			
Haze	%	2.10	ASTM D 1003
Light Transmission	%	89.5	ASTM D 1003
Gloss	%	180	ASTM D 523
Thermal			
Heat Shrinkage	%	MD TD 0.9 0.5	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.
Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com



SH82 (750ga)

Product Information

● **Product Description**

Skyrol® SH82 is an optically clear, glossy, two side chemically treated film. It provides an enhanced adhesion to various inks and adhesives. **SH82** film is available in a range of thickness from 200ga to 750ga, and is used for high quality printing and solvent coating applications.

SH82 film is FDA approved for direct food contact in compliance with FDA 21 CFR 177.1630 (f).

● **Typical Properties**

Property	Unit	Value	Test Method
General			
Nominal Thickness	(Gauge) μm	750 (188)	SKC Method
Mechanical			
Tensile Strength	psi (Kg/mm ²)	MD TD 21,000 (15) 25,500 (18)	ASTM D 882
Elongation At Break	%	MD TD 255 150	ASTM D 882
Surface			
Coefficient of Friction	μk (Kinetic) μs (Static)	0.39 0.43	ASTM D1894
Surface Tension	Dyne	Chemical 36	ASTM D 2578
Optical			
Haze	%	2.70	ASTM D 1003
Light Transmission	%	88.9	ASTM D 1003
Gloss	%	175	ASTM D 523
Thermal			
Heat Shrinkage	%	MD TD 0.9 0.5	SKC Method (150°Cx30 min)

Unit Correlation : N/mm² = Kg/mm² × 9.8

Kg/mm² = psi / 1422.3

SKCA-A-13

This Information is the best currently available on the subject. The results should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's efforts to improve the quality or production efficiency of the subject.

Note: Please read the Material Safety Data Sheet(MSDS) carefully prior to use.

Distributed by:



Piedmont Plastics®

where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com