

TUFFAK GP polycarbonate sheet

GENERAL PURPOSE

TUFFAK GP sheet is a polished surface, UV stabilized, transparent polycarbonate product. It features outstanding impact strength, superior dimensional stability, high temperature resistance, and high clarity. This lightweight thermoflexible sheet is also easy to fabricate and decorate. TUFFAK GP sheet is offered with a five (5) year Limited Product Warranty against breakage. The terms of the warranty are available upon request.

APPLICATIONS

Industrial glazing, machine guards, structural parts, thermoformed and fabricated components

Typical Properties*				
Property	Test Method	Units	Values	
PHYSICAL				
Specific Gravity	ASTM D 792	-	1.2	
Refractive Index	ASTM D 542	-	1.586	
Light Transmission, Clear @ 0.118"	ASTM D 1003	%	86	
Light Transmission, I30 Gray @ 0.118"	ASTM D 1003	%	50	
Light Transmission, K09 Bronze @ 0.118"	ASTM D 1003	%	50	
Light Transmission, I35 Dark Gray @ 0.118"	ASTM D 1003	%	18	
Water Absorption, 24 hours	ASTM D 570	%	0.15	
Poisson's Ratio	ASTM E 132	-	0.38	
MECHANICAL**				
Tensile Strength, Ultimate	ASTM D 638	psi	9,500	
Tensile Strength, Yield	ASTM D 638	psi	9,000	
Tensile Modulus	ASTM D 638	psi	340,000	
Elongation	ASTM D 638	%	110	
Flexural Strength	ASTM D 790	psi	13,500	
Flexural Modulus	ASTM D 790	psi	345,000	
Compressive Strength	ASTM D 695	psi	12,500	
Compressive Modulus	ASTM D 695	psi	345,000	
Izod Impact Strength, Notched @ 0.125"	ASTM D 256	ft-lbs/in	18	
Izod Impact Strength, Unnotched @ 0.125"	ASTM D 256	ft-lbs/in	60 (no break)	
Instrumented Impact @ 0.125"	ASTM D 3763	ft-lbs	47	
Shear Strength, Ultimate	ASTM D 732	psi	10,000	
Shear Strength, Yield	ASTM D 732	psi	6,000	
Shear Modulus	ASTM D 732	psi	114,000	
Rockwell Hardness	ASTM D 785	-	M70 / R118	
THERMAL				
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10-5	
Coefficient of Thermal Conductivity	ASTM C 177	BTU-in/hr-ft ² ·°F	1.35	
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270	
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280	
Brittleness Temperature	ASTM D 746	°F	-200	
Shading Coefficient, clear @ 0.236"	NFRC 100-2010	-	0.97	
Shading Coefficient, Gray or Bronze @ 0.236"	NFRC 100-2010	-	0.77	
U factor @ 0.236" (summer, winter)	NFRC 100-2010	BTU/hr-ft ² ·°F	0.85, 0.92	
U factor @ 0.375" (summer, winter)	NFRC 100-2010	BTU/hr-ft ² ·°F	0.78, 0.85	
ELECTRICAL				
Dielectric Constant @ 10 Hz	ASTM D 150	-	2.96	
Dielectric Constant @ 60 Hz	ASTM D 150	-	3.17	
Volume Resistivity	ASTM D 257	Ohm·cm	8.2 x 1016	
Dissipation Factor @ 60 Hz	ASTM D 150	-	0.0009	
Arc Resistance				
Stainless Steel Strip electrode	ASTM D 495	Seconds	10	
Tungsten Electrodes	ASTM D 495	Seconds	120	
Dielectric Strength, in air @ 0.125"	ASTM D 149	V/mil	380	
FLAMMABILITY				
Horizontal Burn, AEB	ASTM D 635	in	<1	
Ignition Temperature, Self	ASTM D 1929	°F	1022	
Ignition Temperature, Flash	ASTM D 1929	°F	824	
Flame Class @ 0.060"	UL 94	-	HB	
@ 0.394"	UL 94	-	V-0	


Distributed by:



Toll Free: 1.800.277.7898

*Typical properties are not intended for specification purposes.
**Some properties characterized using non-textured sheet.

TUFFAK GP polycarbonate sheet



Standard Products Comparison

Property	Polycarbonate	Acrylic	Glass	
Impact Resistance	Drop Ball Test, 0.5 lb	No Break	1.75 ft-lbs	0.7 ft-lbs
Cold Bend	Bend Radius	100x material thickness	180x material thickness	Not possible
Sheet Weight	0.125"	0.78 lb/ft ²	0.75 lb/ft ²	1.60 lbs/ft ²
Thermal Expansion Rate	–	3.75 x 10 ⁻⁵ in/in/°F	4.10 x 10 ⁻⁵ in/in/°F	5.0 x 10 ⁻⁶ in/in/°F
Shading Coefficient	0.236" clear sheet	0.97	1.01	1.03
U Factor – Summer	0.236"	0.85 BTU/hr·ft ² ·°F	0.83 BTU/hr·ft ² ·°F	0.92 BTU/hr·ft ² ·°F
U Factor – Winter		0.92 BTU/hr·ft ² ·°F	0.91 BTU/hr·ft ² ·°F	1.02 BTU/hr·ft ² ·°F
Sound Transmission Class	0.236"	29	30	27

Regulatory code compliance and certifications

ANSI Z97.1-2009, 2015: American National Standard for Safety Glazing Materials Used in Buildings - Safety Performance Specifications and Methods of Test, Class A, Unlimited

CPSC 16 CFR 1201 Category I and Category II: Safety Standard for Architectural Glazing Materials

Florida Building Code 2017, 6th Ed.

High Velocity Hurricane Zone Classified

Miami-Dade NOA: NOA

ICC-ES Evaluation Report ESR-2728

UL 94: Flammability File #E87887

UL 972: Burglary Resistant Glazing Materials, UL File #BP2126

UL 746C: Suitability for Outdoor Use, UL File #351891*

TUFFAK GP products have limited weathering properties, for more information contact your Plaskolite representative.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.