

Playboard HDPE

Physical	
Density (g/cm ³)	0.960 +
Absorption	Max 0.01%
Hardness, Shore D	69
Mechanical	
Tensile Strength @ Yield (psi)	4,600
Flexural Modulus (psi)	225,000
Notched Izod Impact (ft-lb/in)	120
Elongation at Yeild (%)	>600
Thermal	
Vicat Softening Point (°C)	129
Heat Deflection Temperature @ 66 psi (°C)	82
Coefficient of Linear Thermal Expansion (In./In.°C)	6x10 ⁻⁵
Maximum Service Temperature, Air (°C)	180°F
Low Temperature Brittleness F ₅₀	<-76
Melt Index (g/cm ³)	0.8
Flammability Ratings	
Flammability Rating	UL94 HB



VYCOM
OLEFIN AND PVC SOLUTIONS

Distributed by:



Piedmont Plastics[®]
where solutions take shape

Toll Free: 1.800.277.7898

www.piedmontplastics.com

Physical properties of plastic sheeting are represented as "Typical". Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom; therefore, Vycom disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign.

The "Typical" properties of our plastic sheet cannot be automatically used when engineering finished components; and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!